



PRODUCT DATA SHEET

NZ PAINT CO. LTD
 P.O.BOX 152
 OTAKI 5542
 0800 80 72468

PRODUCT SMS RUBBER PAINT (TWO POT SYSTEM)

Description	SMS A & B is a two pot system, designed for a flexible coating on special rubber surfaces, both interior and exterior and under water.
Uses	For High traffic Butynol & Butyclad Roofing systems, Concrete swimming pools, Garage Floors that are subject to oil, petrol etc. Motor Home renovation and in situations where high elastomeric qualities are required..
Appearance	Gloss
Durability	Suitable for high traffic areas.
Colour Range	White Black Blue or Tinted
Heat Resistance	Up to 120°C
Application	<ol style="list-style-type: none"> 1. Broom or Brush. Recommend first coat to be brushed. 2. Mix A with B at a ratio of 2:1. Stir together. **Important: When mixed a chemical reaction starts that cannot be stopped. The mixed pot life is approx. 3 hours. 3. For floors, Decks and Roof's Recoat 2nd coat to be applied after 24 hours and no later than 36 hours. If the first coat is left longer it will dry so the second coat will delaminate.
Coverage	10m ² per litre
Coating Format	2- 3 coats
Dry Time	3-4 Hours.
Thinner	SMS C
Clean Up	SMS C: to prolong the life of the brushes and other equipment, clean immediately after use with SMS C
Colour Range	Pastel and Deep Tones
Container Sizes	1 Litre and 4 Litre
Surface Preparation	<ol style="list-style-type: none"> 1. As with any product, proper surface preparations is essential for successful application. We emphasise cleanliness on old and new surfaces before paint application, as this is very important to ensure good bonding and lasting quality. 2. Dirt and Grime. Wash and scrub with water. Wash again. Leave to dry. 3. Oily Substances. Clean by rubbing with Enviropaints Special Solvent SMS-C. Allow to dry - you should see a dullness on the rubber if cleaned properly. <p>Caution: Do not use any degreasing agents, waxes or detergents to clean surface before painting</p>
Flash Point	Flammable
Risk Mitigation	<ol style="list-style-type: none"> 1. No protective clothing necessary but good ventilation required. 2. Avoid excessive inhalation of vapour.
Our Suggestions	Do not start the job until you have planned it.

*****Special note: 500ml tin must be added to 1L Part B prior to mixing with Part A**

In the interest of personal safety NZ Paint Co. Ltd recommend all paint products be stored securely away from children. NZ Paint Co. Ltd cares about the environment and our valued customers, if you have any questions on the product you are using from application to disposal or require Material Safety Handling information, please contact NZ Paint Co. free phone (0800) 80 PAINT (72468).

THE information stated on this Data Sheet, to the best of our knowledge is true and accurate. Any recommendations or suggestions are given in good faith but without guarantee since conditions of use and application are beyond NZ Paint Co. Ltd control. Some guarantees may apply by law.